

This potassium-sodium feldspar is typically applied as vitrifying agent, for example in stoneware, clinker and sanitary ware bodies.

MIXED FELDSPAR FSKN

Chemical analysis calcined [%]		
	SiO ₂	76,1
	Al ₂ O ₃	14,9
	TiO ₂	0,03
	Fe ₂ O ₃	0,56
	CaO	0,29
	MgO	0,02
	K ₂ O	3,66
	Na ₂ O	4,37
Loss on ignition [%]		0,79

Mineralogical composition [%]		
	K-Feldspat	21,5
	Na-Feldspat	36,7
	Quarz	31,9
	Kaolinit	9,7

Firing colour		
		lightgrey

Available: • sieved 0-8 mm • ground in the range < 500 µm up to < 63 µm