

White-firing potassium feldspar, ground raw or iron-free, suitable for porcelain, sanitary ware, wall and floor tiles or bright-firing clinker bodies.

### PEGMATITE GP 33

Chemical analysis calcined [%]		
	SiO <sub>2</sub>	85,6
	Al <sub>2</sub> O <sub>3</sub>	9,41
	TiO <sub>2</sub>	0,11
	Fe <sub>2</sub> O <sub>3</sub>	0,10
	CaO	0,01
	MgO	0,02
	K <sub>2</sub> O	3,94
	Na <sub>2</sub> O	0,15
Loss on ignition [%]		1,28

Mineralogical composition [%]		
	K-Feldspat	24,6
	Na-Feldspat	1,6
	Quarz	64,9
	Kaolinit	8,5

Firing colour		
		white

Available: • sieved 0-8 mm • ground in the range < 500 µm up to < 63 µm