

White-firing, ground iron-free and enriched potassium feldspar is suitable, for porcelain bodies or sanitary ware glazes.

PEGMATITE GPA 45

Chemical analysis calcined [%]		
	SiO ₂	82,2
	Al ₂ O ₃	11,1
	TiO ₂	0,12
	Fe ₂ O ₃	0,09
	CaO	0,04
	MgO	0,03
	K ₂ O	6,03
	Na ₂ O	0,28
Loss on ignition [%]		1,01

Mineralogical composition [%]		
	K-Feldspat	36,2
	Na-Feldspat	2,4
	Quarz	54,1
	Kaolinit	7,3

Firing colour		
		white

Available: • sieved 0-8 mm • ground in the range < 500 µm up to < 63 µm