

White-firing, high-percentage feldspar, used as a strong fluxing agent in bright ceramic bodies and glass mixtures.

### SODIUM FELDSPAR FSN-W

Chemical analysis calcined [%]		
	SiO <sub>2</sub>	67,9
	Al <sub>2</sub> O <sub>3</sub>	19,5
	TiO <sub>2</sub>	0,13
	Fe <sub>2</sub> O <sub>3</sub>	0,03
	CaO	1,33
	MgO	0,07
	K <sub>2</sub> O	0,28
	Na <sub>2</sub> O	10,5
Loss on ignition [%]		0,30

Mineralogical composition [%]		
	K-Feldspat	1,6
	Na-Feldspat	89,4
	Quarz	5,2
	Kaolinit	–

Firing colour		
		white

Available: • sieved 0-8 mm • ground in the range < 500 µm up to < 63 µm